

ICC-ES Evaluation Report

ESR-3768

Reissued August 2019

www.icc-es.org | (800) 423-6587 | (562) 699-0543

DIVISION: 06 00 00—WOOD, PLASTICS AND COMPOSITES Section: 06 05 23.13—Nails

REPORT HOLDER:

MITEK USA, INC. 16023 SWINGLEY RIDGE ROAD CHESTERFIELD, MISSOURI 63017 (952) 898-8772 www.mitek-us.com uspcustomerservice@mii.com

EVALUATION SUBJECT:

TECO[®] NAILS

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2018, 2015, 2012 and 2009 *International Building Code*[®] (IBC)
- 2018, 2015, 2012 and 2009 International Residential Code[®] (IRC)
- 2013 Abu Dhabi International Building Code (ADIBC)[†]

 $^{\dagger}\text{The ADIBC}$ is based on the 2009 IBC. 2009 IBC code sections referenced in this report are the same sections in the ADIBC.

Properties evaluated:

- Bending yield strength.
- Compliance with material requirements and tolerances of ASTM F1667.
- Compliance with prescriptive requirements of the IBC and IRC.
- Use in diaphragms, shear walls and braced walls.

2.0 USES

The nails described in this report are used for engineered and prescriptive structural connections between wood members and for attachment of roofing materials to wood sheathing.

3.0 DESCRIPTION

3.1 General:

The nails are formed from plain steel wire of Grades 1006 through 1030. The nails have smooth, ring (annularly threaded) or screw (helically threaded) shanks and concentric round heads.

A Subsidiary of the International Code Council®

This report is subject to renewal August 2021.

3.2 Structural Nails:

See Table 1 for dimensions and additional information for hand-driven nails recognized for use in structural applications, including specified bending yield strength and available finishes. See Table 2 for dimensions and additional information for collated, gun-driven nails recognized for use in structural applications. Dimensional tolerances conform to ASTM F1667.

Some of the sizes of the nails listed in Tables 1 and 2 are available as True Spec brand nails. The True Spec system is intended to allow the shank size and length of a nail to be determined after it is driven, by referring to the nail color and/or the code stamped on the head of the nail. For non-galvanized nails, the length is identified by the paint color on the nail head and the shank diameter is defined by a number. For galvanized nails, the length is identified by a letter and the shank diameter is defined by a number or letter. Non-galvanized nails intended for use with framing connectors (hardware) also have an 'H' on the head. Ring and screw shank nails are identified by an 'r' stamped on the head. See Table 3 for applicable colors and codes.

3.3 Roofing Nails:

Roofing nails have a nominal shank diameter of 11 gage [0.124 inch (3.1 mm)] and a flat round head with a nominal diameter of 0.437 inch (11.1 mm). The nails are available in lengths ranging from ${}^{5}/{}_{8}$ inch to 3 inches (15.9 to 76 mm) and are either hot-dipped galvanized or electro-galvanized. Nail length must comply with the applicable requirements in Section 1507 of the IBC or Section R905 of the IRC. Dimensional tolerances conform to ASTM F1667.

4.0 DESIGN AND INSTALLATION

4.1 Design:

4.1.1 Engineered Structural **Connections:** The structural nails listed in Tables 1 and 2 comply with the requirements of IBC Section 2303.6 and may be used in connections designed in accordance with the ANSI/AWC National Design Specification (NDS) for Wood Construction, using the specified bending yield strengths and nominal nail diameters shown in the tables. For nails with flat round heads and shank diameters that are no more than two-thirds of the head diameter, the reference head pull-through design values must be determined in accordance with Section 12.2.5 of the 2018 NDS. Reference head pull-through design values for other nails are outside the scope of this report. Reference lateral and withdrawal design values for select connections are shown in Table 4. These reference design values must be adjusted by all applicable factors in the NDS.

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.



4.1.2 Engineered Diaphragms and Shear Walls: The structural nails listed in Table 5 comply with the requirements of IBC Section 2303.6 and head area requirements defined in the ICC-ES Acceptance Criteria for Nails (AC116) and are equivalent to the code-prescribed nails listed in Table 5 for use in engineered diaphragms and shear walls in accordance with the AWC Special Design Provisions for Wind and Seismic (SDPWS), which is referenced in the IBC.

4.1.3 Prescriptive Framing Connections: The structural nails listed in Tables 1 and 2 comply with the requirements of IBC Section 2303.6 and may be used in framing connections where the applicable nail type and size is prescribed in IBC Table 2304.10.1 (2012 and 2009 IBC Table 2304.9.1) or IRC Table R602.3(1), as applicable.

4.1.4 Prescriptive Sheathing Attachment: The structural nails listed in Table 5 comply with the requirements of IBC Section 2303.6 and head area requirements of AC116, and are equivalent to the code-prescribed nails listed in Table 5 for attachment of sheathing to wood framing in accordance with IBC Table 2304.10.1 (2012 and 2009 IBC Table 2304.9.1) or IRC Table R602.3(1), as applicable.

4.2 Installation:

4.2.1 Structural Nails: Edge distances, end distances, and spacings must be sufficient to prevent splitting of the wood, and must be in accordance with NDS Section 12.1.6 (2012 NDS Section 11.1.6 for the 2012 IBC; 2005 NDS Section 11.1.5 for the 2009 IBC).

4.2.2 Roofing Nails: Roofing nails must be installed in accordance with IBC Chapter 15 or IRC Chapter 9. When used in roofing applications, the roofing nails must be hot-dipped galvanized in accordance with ASTM A153, Class D.

5.0 CONDITIONS OF USE

The nails described in this report comply with the codes listed in Section 1.0 of this report, subject to the following conditions:

- **5.1** Use of the nails must comply with this report and the applicable code.
- **5.2** When required by the code official, calculations demonstrating that the applied loads are less than

the design values specified by this report must be submitted for approval. Calculations must be prepared by a registered design professional where required by the statutes of the jurisdiction in which the project is to be constructed.

- **5.3** Use of roofing nails must be limited to installation of roof covering materials and other non-structural materials in accordance with IBC Chapter 15 or IRC Chapter 9.
- 5.4 MiTek nails with a hot-dip galvanized coating may be used with preservative-treated wood and fireretardant-treated wood in accordance with 2015 IBC Section 2304.10.5 (2012 and 2009 IBC Section 2304.9.5) and IRC Section 317.3.
- **5.5** Use of the nails with a bright finish in chemicallytreated wood, such as preservative- or fire-retardanttreated wood; or in exterior or exposed conditions, is not permitted.
- **5.6** Use of the electro-galvanized zinc or zinc-phosphate coated nails in chemically-treated wood, such as preservative- or fire-retardant-treated wood; or in exterior or exposed conditions is outside the scope of this report.
- **5.7** The nails are manufactured under a quality control program with inspections by ICC-ES.

6.0 EVIDENCE SUBMITTED

Data in accordance with the ICC-ES Acceptance Criteria for Nails (AC116), dated March 2018.

7.0 IDENTIFICATION

Containers of nails must be identified with the company name (MiTek USA, Inc.) and address; nail type and pennyweight and/or nail size [length and diameter (or gage for roofing nails)]; the finish or coating, and the evaluation report number (ESR-3768). True Spec nails must also be identified as described in Section 3.2 and Table 3.

NAIL TYPE	PENNYWEIGHT	NOMINAL SHANK DIAMETER (inch)	SPECIFIED BENDING YIELD STRENGTH Fyb (psi)	LENGTH (inches)	HEAD STYLE	NOMINAL HEAD DIAMETER (inch)	SHANK TYPE	FINISH ¹
Box	6d / 7d	0.099	100,000	2 / 2 ¹ / ₄	- Flat Round	0.265		
	8d / 9d	0.113		$2^{1}/_{2}/2^{3}/_{4}$		0.297	- Smooth	
	10d / 12d	0.128		3 to $3^{3}/_{4}$		0.312		Bright, VC, EG, Phos, HDG
	16d	0.135		3 ¹ / ₂		0.344		
	20d / 30d	0.148	90,000	4 to $4^{1}/_{2}$		0.375		
	40d	0.162		5		0.406		
	6d / 7d	0.099	1	2 / 2 ¹ / ₄	Countersunk, cupped	0.142	- Smoot h	HDG
Casing	8d	0.113	100.000	2 ¹ / ₂		0.155		
Casing	10d / 12d	0.131	100,000	3 / 3 ¹ / ₄		0.170		
	16d	0.135		3 ¹ / ₂		0.177		
Common	4d / 5d	0.099		1 ¹ / ₂ / 1 ³ / ₄	- Flat Round	0.250	Smooth Ring	Bright, VC, HDG
	6d / 7d	0.113	100,000	2 / 2 ¹ / ₄		0.265		
	8d / 9d	0.131		2 ¹ / ₂ / 2 ³ / ₄		0.281		
	10d / 12d	0.148	90,000	3 / 3 ¹ / ₄		0.312		
	16d	0.162		3 ¹ / ₂		0.344		
	20d	0.192	80,000	4		0.406		
		0.120	100,000	$1^{1}/_{4}$ to $1^{1}/_{2}$		0.297		Bright, EG, HDG
	n/a	0.120		1 ¹ / ₂ , 2 ¹ / ₂ Round	0.281	Smooth	Bright HDC	
Hardware		0.131			Round	0.201	Ring	Blight, HDG
		0.148	90,000	$1^{1}/_{4}$ to $1^{1}/_{2}$		0.312	Screw	Bright, EG,
		0.162		2 ¹ / ₂		0.344		HDG
		0.192	80,000	2 ¹ / ₂		0.375		HDG
Finishing	8d	0.099	100,000	2 ¹ / ₂	Brad	0.142	Smooth	
	10d / 12d	0.113		3 / 3 ¹ / ₄		0.155		Bright UDC
	16d	0.120		3 ¹ / ₂		0.162		Blight, HDG
	20d	0.135		4		0.177		
Sinker	7d	0.099	100,000	2 ¹ / ₈	Flat countersunk	0.250	Smooth	
	8d	0.113		2 ³ / ₈		0.266		
	10d	0.120		2 ⁷ / ₈		0.281		VC, Phos, HDG
	12d	0.135]	3 ¹ / ₈		0.312		
	16d	0.148	90,000	3 ¹ / ₄		0.344		

TABLE 1—HAND DRIVEN STRUCTURAL NAILS

For **SI:** 1 inch = 25.4 mm, 1 psi = 6.89 kPa.

¹Finish types:

Bright VC EG Phos HDG Non-galvanized Vinyl-coated =

=

=

Zinc-coated (Electro-galvanized) Zinc-phosphate coated Zinc –coated (Hot-dipped galvanized) complying with ASTM A153 Class D = =

NOMINAL SHANK DIAMETER (inch)	SPECIFIED BENDING YIELD STRENGTH Fyb (psi)	RANGE OF LENGTHS (inch)	HEAD STYLE	NOMINAL HEAD DIAMETER (inch)	SHANK TYPE ¹	FINISH ²
0.113		$1^{1}/_{2}$ to $2^{1}/_{2}$	Flat Round	0.275	S, R, Sc	Bright, EG, HDG
0.120	100,000	2 to $3^{1}/_{4}$		0.275	S, R, Sc	Bright, EG, HDG, HT
0.131		$1^{1}/_{2}$ to $3^{1}/_{2}$		0.285	S, R, Sc	Bright, EG, HDG, HT
0.135		$2^{1}/_{4}$ to $3^{1}/_{2}$		0.285	S, R, Sc	Bright, EG, HDG, HT
0.148	00.000	$1^{1}/_{2}$ to 4		0.285	S, R, Sc	Bright, EG, HDG, HT
0.162	0.162			0.290	S, R, Sc	Bright, EG, HDG, HT

TABLE 2—GUN DRIVEN STRUCTURAL NAILS

For **SI:** 1 inch = 25.4 mm, 1 psi = 6.89 kPa.

¹Shank types: S = smooth, R = ring, Sc = screw ²Finish types:

Bright = EG = Non-galvanized

Zinc-coated (Electro-galvanized)

HDG Zinc -coated (Hot-dipped galvanized) complying with ASTM A153 Class D =

ΗT = Heat Treated

TABLE 3—TRUE SPEC HEAD IDENTIFICATION SYSTEM LEGEND¹

DIAMETER INDICATOR						
Nominal Shank Diameter	Indicator for Smooth Shank and Screw Shank Nails, All Finishes	Indicator for Ring Shank Nails with HDG Finish				
0.113	1	Т				
0.131	3	W				
0.135	5	X				
0.148	4	Y				
0.162	6	Z				
LENGTH INDICATOR						
Length (Inches)	Indicator for Non-Galvanized Nails	Indicator for HDG Nails				
1 ¹ / ₂	Purple	A				
2 ¹ / ₈	Pink	В				
2 ¹ / ₄	Brown	С				
2 ³ / ₈	Green	D				
2 ¹ / ₂	Blue	E				
3	White	F				
3 ¹ / ₄	Black	J				
3 ¹ / ₂	Orange	К				

For **SI:** 1 inch = 25.4 mm, 1 psi = 6.89 kPa.

¹Non-galvanized nails intended for use with framing connectors (hardware) also have an 'H' on the head. Ring and screw shank nails are identified by an 'r' stamped on the head.

TABLE 4—SINGLE FASTENER CONNECTIONS—REFERENCE DESIGN VALUES (LATERAL AND WITHDRAWAL)^{1,+}

	REFERENCE	LATERAL DESIGN	REFERENCE WITHDRAWAL DESIGN VALUE (Ibf per inch) ³		
DIAMETER (inch)	Minimum Side Member Thickness (inches)	Southern Pine SG = 0.55	Douglas Fir– Larch SG = 0.50	Southern Pine SG = 0.55	Douglas Fir– Larch SG = 0.50
0.099	³ / ₄	61	55	31	24
0.113	³ / ₄	79	72	35	28
0.120	1	89	81	37	29
0.128	1	101	93	40	31
0.131	1	106	97	41	32
0.135	1	113	103	42	33
0.148	1	128	118	46	36
0.162	1	154	141	50	40
0.192	1	183	159	59	47

For SI: 1 inch = 25.4 mm, 1 lbf = 4.45 N; 1 lbf/inch = 0.175 N/mm.

¹Tabulated nominal values must be multiplied by all applicable adjustment factors in accordance with the NDS.

²Tabulated lateral design values are for connections of members with identical specific gravity and nails inserted in side grain with nail axis perpendicular to wood fibers; minimum nail penetration into the main member must equal 10 diameters. ³Tabulated nominal withdrawal values are for nails driven in the side grain of the main member, with the nail axis perpendicular to the wood

fibers.

⁴For diameters other than those noted, withdrawal values must be the same as for the smooth nails.

⁵References: Lateral design values—2018 NDS Table 12N. Withdrawal design values—2018 NDS Table 12.2C.

TABLE 5—STRUCTURAL NAILS RECOGNIZED FOR USE IN ENGINEERED DIAPHRAGMS AND SHEAR WALLS AND PRESCRIPTIVE SHEATHING ATTACHMENTS

NAIL TYPE AND SIZE PRESCRIBED IN	MITEK USA, INC. CONNECTORS NAIL DESCRIPTION (RECOGNIZED EQUIVALENT)				
THE CODE	Hand Driven (See Table 1)	Gun Driven (See Table 2)			
6d common (2" x 0.113")	8d box; 6d and 7d common; 8d sinker	2 to 2 ¹ / ₂ " x 0.113"			
8d common (2 ¹ / ₂ " x 0.131")	10d box; 8d and 9d common	2 ¹ / ₂ " to 3" x 0.131"			
10d common (3" x 0.148")	10 and 12d common; 16d sinker	3" to 3 ¹ / ₄ " x 0.148"			

For SI: 1 inch = 25.4 mm.